# Lincolnweld® L-61®

AWS EM12K • Mild Steel Solid Electrode

### **Conformances**

AWS A5.17/A5.17M: 1997 EM12K MIL-E-23765/4: MIL-EM12K EN 756: S2Si

## **Key Features**

- Industry standard for submerged arc welding applications
- ▶ A low carbon, medium manganese, low silicon general purpose submerged arc electrode
- ▶ A good choice for a wide range of applications with single or multiple pass subarc welding

# **Recommended Fluxes**

Lincolnweld® 760®, 761®, 780®, 781 $^{\text{TM}}$ , 860®, 865 $^{\text{TM}}$ , 882 $^{\text{TM}}$ , 888 $^{\text{TM}}$ , 761-Pipe $^{\text{TM}}$ , P223 $^{\text{TM}}$ , 960®, 980 $^{\text{TM}}$ , WTX $^{\text{TM}}$ , AXXX-10 $^{\text{TM}}$ , 995N $^{\text{TM}}$ , SPX80 $^{\text{TM}}$ 

### **DIAMETERS / PACKAGING**

DIAMETERO / FACILAGINA									
Diameter in. (mm)	60 lb (27.2 kg) Coil	250 lb (113 kg) Speed Feed® Reel	300 lb (136 kg) Speed Feed® Reel	300 lb (136 kg) Speed Feed® Drum					
1/16 (1.6) 5/64 (2.0) 3/32 (2.4) 1/8 (3.2) 5/32 (4.0) 3/16 (4.8)	ED011803 ED011825 ED011815 ED011807 ED011821 ED011812	ED033074 ED033075 ED033076	ED030412	ED030628					
Diameter in. (mm)	600 lb (272 kg) Speed Feed® Drum	750 lb (340 kg) Speed Feed® Reel	1000 lb (453 kg) Speed Feed® Drum	2200 lb (998 kg) Speed Feed® Stem					

# **WIRE COMPOSITION**(1) - As Required per AWS A5.17/A5.17M:1997

	%C	%Mn	%Si	%S	%P	%Cu
Lincolnweld® L-61®	0.05-0.15	0.80-1.25	0.10-0.35	0.030	0.030	0.35

<sup>(1)</sup>Single values are maximums.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

#### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

#### CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change - This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.

