

OK Autrod 308L

SAW
ER308L

Description

A continuous, solid, corrosion-resistant, chromium-nickel wire. OK Autrod 308L has good general corrosion resistance. The alloy has a low carbon content which makes it particularly recommended where there is a risk of intergranular corrosion. The alloy is widely used in the chemical and food-processing industries, as well as for pipes, tubes and boilers. OK Autrod 308L can be used in combination with OK Flux 10.93 or OK Flux 10.92.

Classifications

SFA/AWS A5.9	ER308L
EN 12072	S 19 9 L

Wire composition (%)

C	Si	Mn	Cr	Ni	Mo	Cu
<0.03	0.5	1.8	20.3	10.0	<0.3	<0.3